

TEST REPORT

LAB NO.: 2002257/1-3

DATE: 31/07/2020

NAME OF CUSTOMER

: GREENLAM INDUSTRIES LIMITED

ADDRESS

: Vill. Paterh Bhonku, PO Panjehra, Teh. Nalagarh, Distt. Salon,

Himachal Pradesh – 174 101

REFERENCE

: Your Letter Ref. Nil dated July 11, 2020

DATE OF RECEIPT

: 11/07/2020

DATE OF INITIATION

: 11/07/2020

DATE OF COMPLETION

: 31/07/2020

SAMPLE DESCRIPTION

: Laminate Sample specimen labeled as -

Sr. No.	Description
1.	Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113
2.	Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141

Name of Test:

Measurement of Antiviral activity on plastics and other non-porous surfaces

Name of Test Protocol:

ISO 21702: 2019*

Scope of Method:

This test specifies method for measuring antiviral activity on plastic and other non-porous surface of antiviral-treated products against specified virus. Due to individual sensitivities, the results of one test virus might not be applicable for other viruses.

*Modified method with use of MS2 virus

Page 1 of 4

[•] Samples are not drawn by the laboratory • Result relate only to the samples tested • This report shall not be reproduced except in full without prior permission of this laboratory



Test Microorganism Information:

MS2 Bacteriophage (MS2) is an RNA virus of the family Leviviridae. Escherichia coli 15597 are the hosts for bacteriophages. Due to its environmental resistance, MS2 bacteriophages are used as a surrogate virus (particularly in place of Picornaviruses such as Poliovirus and human Norovirus) in water quality and Antimicrobial studies.

Virus: MS2 Bacteriophage

Permissive Host Cell: Escherichia coli ATCC 15597

Experimental Details:

Test Carrier

: Panel surface (50 mm x 50 mm); Pre-sterilized by UV light

Control Carrier

: Panel pre sterilized (50 mm x 50 mm)

LDPE cover

: LDPE film pre sterilized 40 mm x 40 mm

Virus

: MS2 Bacteriophage; Inoculum volume 0.4 ml

Permissive Host Cell

: Escherichia coli ATCC 15597

Contact Period

: 2 hours and 24 hours

Neutralizer

: DE broth

Medium

: Trypticase soya agar

Incubation for survivors

: 37°C for 3 days

Validation and Records:

Neutralizer Validation and Records:

Validation Test							
Test Organism	Exptl. Condition Control (A) (CFU/ ml)	Neutralizer Toxicity Control (B) (CFU/ ml)	Dilution-neutralization Control © (CFU/ ml)				
MS2 Bacteriophage	50	52	58				

Where -

A=No. of PFU/ml of Test organism in Experimental condition validation B=No. of PFU/ml of Test organism in Neutralizer Toxicity validation

2002257/1-2 Page 2 of 4

[•] Samples are not drawn by the laboratory • Result relate only to the samples tested • This report shall not be reproduced except in full without prior permission of this laboratory



BIOTECH TESTING SERVICES

Test Procedure:

Pre-sterilized samples were loaded with diluted viral suspension to 10⁶ PFU/ ml. Virus suspension 0.4 ml was added to 50 mm x 50 mm of Test substrate. It was covered with 40 mm x 40 mm LDPE film. Following exposure time, Virus was eluted and neutralized by serial tenfold dilution and assayed to determined surviving Viruses in comparison with Control without test product in sq. cms. Virus assay was quantitative as Plaque forming unit (PFU) visible as area of Clearance.

Results:

A: 2 HOURS

·	Quantitative Assessme	ent of Antiviral Activi	ity – ISO 21702: 2019	V
Untreated: Average no.	Log = 4.77			
Untreated: Average no.	Log = 4.85			
Sample Identification	Average No. of Plaques recovered from Treated (At)	Log of Plaques recovered from Treated (At)	Antiviral Activity (R) (Log U _t - A _t)	Virus Reduction Percentage
Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113	620	2.79	2.06	99.12
Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141	7300	3.86	0.99	89.71

B: 24 HOURS

Quantitative Assessment of Antiviral Activity – ISO 21702: 2019							
Untreated: Average no.	Log = 4.77						
Untreated: Average no.	Log = 4.95						
Sample Identification	Average No. of Plaques recovered from Treated (At)	Log of Plaques recovered from Treated (At)	Antiviral Activity (R) (Log U _t - A _t)	Virus Reduction Percentage			
Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113	90	, 1.95	3.00	99.90			
Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141	1560	3.19	1.76	98.26			

Where:

R = Antiviral activity

 U_0 = Log of PFU recovered from Untreated specimen immediately after inoculation, in PFU/ cm²

 U_t = Log of PFU recovered from Untreated specimen after 2/ 24 hrs. after inoculation, in PFU/ cm²

At = Log of PFU recovered from Treated specimen after 2/24 hrs. after inoculation, in PFU/cm²

2002257/1-2 Page 3 of 4

Samples are not drawn by the laboratory
 Result relate only to the samples tested
 This report shall not be reproduced except in full without prior permission of this laboratory



COMMENT:

When tested as specified, laminate sample labeled as Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113 has shown 99.12% and 99.90% Reduction; Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141 has shown 89.71% and 98.26% Reduction of virus in 2 hours and 24 hours when tested by ISO 21702: 2019 standard.



For BIOTECH TESTING SERVICES

Dr Shilpa U. Nair Quality Manager (Authorized Signatory)

> 2002257/1-2 Page 4 of 4

• Samples are not drawn by the laboratory • Result relate only to the samples tested • This report shall not be reproduced except in full without prior permission of this laboratory